



MAKROLON® 2805 and 2856

Polycarbonate Resins

2805 General-Purpose Grade with release

2856 FDA-Food Contact Quality Grade with release

Description

Makrolon 2805 and 2856 polycarbonate resins are linear, medium-viscosity, high-performance thermoplastics produced in pellet form for processing primarily by injection molding. Both grades contain an internal mold release additive. The resins are available in natural, clear tints, select transparent, translucent, opaque colors and special effects.

In addition, Makrolon 2856 resin complies with FDA food-contact regulations 21 CFR 177.1580 (Polycarbonate Resins) and may be used in contact with all food types. Most colors may be used for all thermal food-contact applications. However, some colors are limited by Conditions of Use B through H, 21 CFR 175.300 and 176.170 and may not be used when the food is sterilized in the food-contact article under autoclaving conditions. Please contact your Bayer MaterialScience representative with complete details when food contact is involved.

Makrolon 2856 resin, in natural 000000 and clear tints 550042 and 550115, is also listed under NSF standard 51 for use in food equipment. Please consult your Bayer MaterialScience representative for more information about food equipment applications.

Applications

Makrolon 2805 and 2856 polycarbonate resins have an excellent balance of engineering properties, including outstanding impact strength and ductility, a wide range of service temperatures, excellent electrical properties and

dimensional stability. Makrolon 2805 and 2856 resins are used in the automotive industry, building and construction, business equipment, consumer products, electronics and telecommunications, lighting, packaging, optical devices, optical lenses, and photographic equipment.

As with any product, use of Makrolon 2805 and 2856 resins in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability. The suitability of a Bayer product in a given end-use environment is dependent upon various conditions including, without limitation, chemical compatibility, temperature, part design, residual stresses, and external loads. It is the responsibility of the Manufacturer to evaluate its final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Drying

All polycarbonate resins are hygroscopic and must be thoroughly dried prior to processing. A desiccant dehumidifying hopper dryer is recommended. To achieve a moisture content of less than 0.02%, hopper inlet air temperature should be 250°F (121°C) and inlet air dew point should be -20°F (-29°C) or lower. The hopper capacity should be sufficient to provide a minimum residence time of 4 hours. Additional information on drying procedures is available in the Bayer brochure *General Drying Guide*.

Processing

Makrolon 2805 and 2856 polycarbonate resins may be easily processed on commercially available molding equipment suitable for injection molding of polycarbonate. Processing parameters are listed in the “Typical Injection Molding Conditions” table. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, etc.

Typical Injection Molding Conditions	
Barrel Temperatures:	
Rear	500°–540° F (260°–282° C)
Middle	530°–570° F (277°–299° C)
Front	555°–595° F (291°–313° C)
Nozzle	535°–595° F (279°–313° C)
Melt Temperature	560°–590° F (293°–310° C)
Mold Temperature	150°–220° F (66°–104° C)
Injection Pressure	10,000–20,000 psi
Hold Pressure	50–70% of Injection Pressure
Shot Size	25–75% of Barrel Capacity
Back Pressure	50–100 psi
Screw Speed	50–75 rpm
Injection Speed	Moderate to Fast
Cushion	1/8–1/4 in
Clamp	3–5 ton/in ²

Additional information on processing may be obtained by consulting the Bayer publication *Makrolon Polycarbonate — A Processing Guide for Injection Molding* and by contacting a Bayer MaterialScience technical service representative.

Regrind Information

Where end-use requirements permit, up to 20% Makrolon resin regrind may be used with virgin material, provided that the material is kept free of contamination and is properly dried (see section on Drying). Any regrind used must be generated from properly molded parts, sprues, and/or runners. All regrind used must be clean, uncontaminated, and thoroughly blended with virgin resin prior to drying and processing. Under no circumstances should degraded, discolored, or contaminated material be used for regrind. Materials of this type should be properly discarded.

Improperly mixed and/or dried regrind may diminish the desired properties of Makrolon resin. It is critical that you test finished parts produced with any amount of regrind to ensure that your end-use performance requirements are fully met. Regulatory or testing organizations (e.g., UL) may have specific requirements limiting the allowable amount of regrind. Because third party regrind generally does not have a traceable heat history or offer any assurance that proper temperatures, conditions, and/or materials were used in processing, extreme caution must be exercised in buying and using regrind from third parties. Third party regrind must not be used in end-uses that are to comply with FDA's food-contact regulations.

The use of regrind material should be avoided entirely in those applications where resin properties equivalent to virgin material are required, including but not limited to color quality, impact strength, resin purity, and/or load-bearing performance.

Typical Properties* for Natural Resin	ASTM Test Method (Other)	Makrolon® 2805/2856 Resins	
		U.S. Conventional	SI Metric
General Specific Gravity Density Specific Volume Mold Shrinkage Water Absorption, Immersion at 73°F (23°C): 24 Hours Equilibrium Melt Flow Rate ^a at 300°C/1.2-kg Load	D 792 D 792 D 792 D 955 D 570 D 1238	0.043 lb/in ³ 23.1 in ³ /lb 0.006–0.008 in/in	1.20 0.12% 0.30% 10 g/10 min
Optical Transmittance at 0.125-in (3.2-mm) Thickness Haze at 0.125-in (3.2-mm) Thickness Refractive Index	D 1003 D 1003 D 542		88% <0.8% 1.586
Mechanical^b Tensile Stress at Yield Tensile Stress at Break Tensile Elongation at Yield Tensile Elongation at Break Tensile Modulus (1 mm/min) Flexural Stress at 5% Strain Flexural Modulus Compressive Stress at Yield Impact Strength, Notched Izod: 73°F (23°C) 0.125-in (3.2-mm) Thickness Tensile Impact Strength, "S" Specimen: 0.125-in (3.2-mm) Thickness Rockwell Hardness: M Scale R Scale	D 638 D 638 D 638 D 638 D 638 D 790 D 790 D 695 D 256 D 1822 D 785	9,400 lb/in ² 10,200 lb/in ² 350,000 lb/in ² 12,500 lb/in ² 340,000 lb/in ² 11,000 lb/in ² 17 ft-lb/in 275 ft-lb/in ²	65 MPa 70 MPa 2.4 GPa 86 MPa 2.4 GPa 76 MPa 908 J/m 575 kJ/m ² 75 120
Thermal Deflection Temperature, Unannealed: 0.250-in (6.4-mm) Thickness 264-psi (1.82-MPa) Load 66-psi (0.46-MPa) Load Coefficient of Linear Thermal Expansion Thermal Conductivity Specific Heat Relative Temperature Index: 0.059-in (1.5-mm) Thickness Electrical Mechanical with Impact Mechanical without Impact Vicat Softening Temperature, 50 N, 50°C/h	D 648 D 696 C 177 D 2766 (UL746B) D 1525	268°F 280°F 3.34 E-05 in/in/°F 1.39 Btu-in/(h-ft ² -°F) 0.28 Btu/(lb-°F)	131°C 138°C 6.0 E-05 mm/mm/°C 0.20 W/(m-K) 1,172 J/(kg-K) 125°C 115°C 125°C 144°C
Flammability** Oxygen Index UL94 Flame Class: 1.5-mm (0.059-in) Thickness 2.5-mm (0.098-in) Thickness 6.0-mm (0.236-in) Thickness	D 2863 (UL94)		28% V-2 Rating HB Rating HB Rating
Electrical Volume Resistivity (Tinfoil Electrodes) Surface Resistivity Dielectric Strength (Short Time Under Oil at 1-mm [0.04-in] and 73°F [23°C]) Dielectric Constant (Tinfoil Electrodes): 60 Hz 1 MHz Dissipation Factor (Tinfoil Electrodes): 60 Hz 1 MHz Arc Resistance: Stainless Steel Electrodes Tungsten Electrodes	D 257 D 257 D 149 D 150 D 150 D 495	810 V/mil	1.0 E+16 ohm-cm 1.0 E+16 ohm 3.0 2.9 0.0009 0.01 11 s 120 s

* These items are provided as general information only. They are approximate values and are not part of the product specifications.

** Flammability results are based on small-scale laboratory tests for purposes of relative comparison and are not intended to reflect the hazards presented by this or any other material under actual fire conditions.

^a For information on using melt flow as a quality control procedure, see the Bayer publication Makrolon Polycarbonate — A Processing Guide for Injection Molding.

^b Type and quantity of pigment used in opaque colors can affect mechanical properties, especially toughness.

General Characteristics of Polycarbonate

Hydrolytic Stability: Parts molded from polycarbonate absorb only 0.15 to 0.19% water at room temperature and 50% relative humidity. Dimensional stability and mechanical properties remain virtually unaffected. Even with immersion in water, dimensional changes measure only about 0.5%. Although frequent, intermittent contact with hot water does not harm polycarbonate, continuous exposure to humidity or water at high temperatures (>140°F/60°C) is not recommended due to hydrolytic degradation, which reduces impact strength and tensile properties.

Gas Permeability: Steam permeability, measured on 100- μ m thick film, is 15 g/m²·24 h (0.97 g/100 in²·24 h). Significant permeability also exists for other gases, such as hydrogen, carbon dioxide, sulfur dioxide, helium, ethylene oxide, and oxygen.

Chemical Resistance: Polycarbonate is resistant to mineral acids (even in high concentrations), a large number of organic acids, many oxidizing and reducing agents, neutral and acidic saline solutions, some greases and oils, saturated aliphatic and cycloaliphatic hydrocarbons, and most alcohols. It is important to note that polycarbonate is degraded by alkaline solutions, ammonia gas and its solutions, and amines.

Polycarbonate dissolves in a number of organic solvents, such as halogenated hydrocarbons and some aromatic hydrocarbons. Other organic compounds cause polycarbonate to swell or stress-crack, e.g., acetone

and methyl ethyl ketone. Since chemical resistance to various media is dependent on variables, such as concentration, time, temperature, part design, and residual stresses, the above information should serve only as a guideline. It is imperative that production parts be evaluated under actual application conditions prior to commercial use.

Regulatory Compliance Information

Some of the end uses of the products described in this bulletin must comply with applicable regulations, such as FDA, NSF, USDA, and CPSC. If you have any questions on the regulatory status of these products, contact your Bayer MaterialScience representative or Bayer's Regulatory Affairs Manager in Pittsburgh, PA.

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the Makrolon resins described in this bulletin. Before working with these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets and product labels. Consult your Bayer MaterialScience representative or contact Bayer's Product Safety and Regulatory Affairs Department in Pittsburgh, PA

Note: The information contained in this bulletin is current as of September 2007. Please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-412-777-2000 • www.BayerMaterialScienceNAFTA.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Sales Offices

1000 Route 9 North, Suite 103, Woodbridge, NJ 07095-1200 • 1-732-726-8988 • Fax: 1-732-726-1672
2401 Walton Boulevard, Auburn Hills, MI 48326-1957 • Phone: 1-248-475-7700 • Fax: 1-248-475-7701
